

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
30 June 2005 (30.06.2005)

PCT

(10) International Publication Number  
**WO 2005/058978 A1**

(51) International Patent Classification<sup>7</sup>: **C08F 4/647**,  
2/00, 10/00

(21) International Application Number:  
PCT/GB2004/005197

(22) International Filing Date: 8 December 2004 (08.12.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0329348.7 18 December 2003 (18.12.2003) GB

(71) Applicant (for all designated States except US): **BP  
CHEMICALS LIMITED** [GB/GB]; Chertsey Road,  
Sunbury-on-Thames, Middlesex TW16 7BP (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KIMBERLEY,  
Brian, Stephen** [GB/FR]; 1116, rue Camille Saint Saens,  
Bouc-Bel-Air, F-13320 Bouche Du Rhone (FR). **LA-  
CANE, Gerard** [FR/FR]; 10, rue de Figueras, F-13700  
Marignane (FR). **MASTROIANNI, Sergio** [FR/BE];  
Cours Saint Michel 92, B-1040 Etterbeek (BE).

(74) Agent: **HAWKINS, David, George**; O & D Trading  
Limited, Patents and Agreements, Compass Point, 79-87  
Kingston Road, Staines, Middlesex TW18 1DT (GB).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,

MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,  
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,  
GQ, GW, ML, MR, NE, SN, TD, TG).

**Declarations under Rule 4.17:**

- as to applicant's entitlement to apply for and be granted  
a patent (Rule 4.17(ii)) for the following designations AE,  
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ,  
CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE,  
EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS,  
JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,  
MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM,  
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ,  
TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM,  
ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA,  
SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ,  
BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,  
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,  
IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR),  
OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,  
ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

**Published:**

- with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: POLYMERISATION PROCESS

(57) Abstract: A process for the polymerisation of olefin monomers selected from (a) ethylene, (b) propylene (c) mixtures of ethylene and propylene and (d) mixtures of (a), (b) or (c) with one or more other alpha-olefins is performed in a polymerisation reactor in the presence of a supported polymerisation catalyst characterised in that prior to injection into the reactor said supported polymerisation catalyst in the form of a powder is contacted with an inert hydrocarbon liquid in a quantity sufficient to maintain said catalyst in powder form. The preferred inert hydrocarbon liquid is hexane. The supported polymerisation catalyst is preferably a supported metallocene catalyst. According to the process of the present invention the level of fines associated with the polymer products is reduced in particular the level of fines having a diameter < 125 µm and microfines of diameter < 50 µm.



WO 2005/058978 A1